

# **Touch Up Pen / Bottle**

### Step 1 - Shake

Shake bottle/ pen thoroughly for at least 60 seconds. For the needle point pens – remove the clear lid with a firm pull. Unscrew the white collar to access the brush.

If there's any doubt on colour match test in discreet area and let dry for 10 minutes – paints will often appear different in colour in the bottle, when wet or if applied incorrectly.

### Step 2 - Prepare

The surface must be clean and dry - make sure all wax, polish and dust is removed. If you have a deep scratch or chip OR if you can see metal or plastic we recommend using a primer first - if rust is present we suppost a rust freatment as well.

### Step 3 - Paint

Using either pen or brush apply thin, light coats in smooth strokes; if you're using the needle point pen allow the nib to sit in the scratch or chip and squeeze gently.

Leave paint to dry for 10-25 minutes before applying a second coat if required. Leave paint to cure for 24 hours till hardened before applying lacquer or polishing.



# **Aerosol Paint**

### Step 1 - Shake

Shake aerosof for at least 2 minutes. Before spraying the vehicle we recommend testing the colour – our body shop quality adjustable nozzle allows you to spray either horizontally or vertically.

## Step 2 - Prepare

- 2a) It is always advisable to flatten down the area first using a wet and dry sand paper.
- 2b) The surface must be clean and dry make sure all wax, polish and dust is removed.
- 2c) In most repairs we would recommend using a primer.

### Step 3 - Paint

Either vertically or horizontally apply in smooth cross coats 250mm distance from the repair.

Leave to dry for 15 minutes before applying a second coat if necessary and leave 24 hours before applying lacquer.

After use turn aerosol upside down to empty nozzle valve to clean then it can be reused at a later date

